

External_Type	Material_Group	Substances	CAS_Number	Mass	Mass_Percentage_in_Leaf	Massmg
Wire	Pure metal	Gold (Au)	7440-57-5	0.04618	100.0	0.105
Subtotal				0.04618	100	0.105
Post-plating	Tin solder	Bismuth (Bi)	7440-69-9	0	0.0	0
	Tin solder	Tin (Sn)	7440-31-5	1.61845	99.99	3.67963
	Tin solder	Copper (Cu)	7440-50-8	0	0.0	0
	Tin solder	Lead (Pb)	7439-92-1	0.00016	0.01	0.00037
	Tin solder	Antimony (Sb)	7440-36-0	0	0.0	0
Subtotal				1.61861	100	3.68
Lead Frame	Copper alloy	Misc. Phosphor compounds (generic)	7723-14-0	0.00789	0.02	0.01794
	Copper alloy	Iron (Fe)	7439-89-6	0.03157	0.08	0.07178
	Copper alloy	Copper (Cu)	7440-50-8	39.34413	99.7	89.45084
	Pure metal layer	Silver (Ag)	7440-22-4	0.07893	0.2	0.17944
Subtotal				39.46252	100	89.72
Adhesive	Polymer	Paraffin wax	8002-74-2	0.21992	20.0	0.5
	Polymer	Epoxy resin system		0.08797	8.0	0.2
	Filler	Silver (Ag)	7440-22-4	0.79171	72.0	1.8
Subtotal				1.0996	100	2.5
Mould Compound	Polymer	Tetrabromobisphenol A/Epichlorohydrin polymer	40039-93-8	1.43905	2.5	3.27175
	Polymer	Phenol Formaldehyde resin (generic)	9003-35-4	4.31715	7.5	9.81525
	Filler	Silica -amorphous-	7631-86-9	21.29793	37.0	48.4219
	Pigment	Carbon black	1333-86-4	0.28781	0.5	0.65435
	Polymer	Epoxy resin system		8.63429	15.0	19.6305
	Filler	Silicon Dioxide (SiO2)	14808-60-7	21.29793	37.0	48.4219
	Flame retardant	Antimony Trioxide (Sb2O3) - cas no. 1309-64-4	1309-64-4	0.28781	0.5	0.65435
Subtotal				57.56197	100	130.87
Die	Doped silicon	Silicon (Si)	7440-21-3	0.19793	100.0	0.45
Subtotal				0.19793	100	0.45
Wire	Pure metal	Copper (Cu)	7440-50-8	0.0132	100.0	0.03
Subtotal				0.0132	100	0.03
Total				100.00001	100	227.355

Disclaimer

All information in this document is furnished for exploratory or indicative purposes only. All information in this document is believed to be accurate and reliable. However, WeEn Semiconductors does not give any representations or warranties as to the accuracy or completeness of such information and shall have no liability for the consequences of use of such information. WeEn Semiconductors may make changes to information published in this document at any time and without notice. Minor deviations may occur in the products from different manufacturing location. This document supersedes and replaces all information supplied prior to the publication hereof. Nothing in this document may be interpreted or construed as an offer to sell products that is open for acceptance or the grant, conveyance or implication of any license under any copyrights, patents or other industrial or intellectual property rights.