

External_Type	Material_Group	Substances	CAS_Number	Mass	Mass_Percentage_in_Leaf	Massmg
Die	Doped silicon	Silicon (Si)	7440-21-3	0.39406	100.0	0.91
Subtotal				0.39406	100	0.91
Post-plating	Tin solder	Bismuth (Bi)	7440-69-9	0	0.0	0
	Tin solder	Tin (Sn)	7440-31-5	1.5934	99.99	3.67963
	Tin solder	Copper (Cu)	7440-50-8	0	0.0	0
	Tin solder	Lead (Pb)	7439-92-1	0.00016	0.01	0.00037
	Tin solder	Antimony (Sb)	7440-36-0	0	0.0	0
Subtotal				1.59356	100	3.68
Lead Frame	Copper alloy	Phosphorous (P)	7723-14-0	0.01203	0.03	0.02778
	Copper alloy	Iron (Fe)	7439-89-6	0.0401	0.1	0.0926
	Copper alloy	Copper (Cu)	7440-50-8	39.93834	99.6	92.2296
	Pure metal layer	Silver (Ag)	7440-22-4	0.10827	0.27	0.25002
Subtotal				40.09874	100	92.6
Adhesive	Polymer	Paraffin wax	8002-74-2	0.19833	20.0	0.458
	Polymer	Epoxy resin system		0.07933	8.0	0.1832
	Filler	Silver (Ag)	7440-22-4	0.71398	72.0	1.6488
Subtotal				0.99164	100	2.29
Mould Compound	Polymer	Tetrabromobisphenol A/Epichlorohydrin polymer	40039-93-8	1.42283	2.5	3.28575
	Polymer	Phenol Formaldehyde resin (generic)	9003-35-4	4.2685	7.5	9.85725
	Filler	Silica -amorphous-	7631-86-9	21.05794	37.0	48.6291
	Pigment	Carbon black	1333-86-4	0.28457	0.5	0.65715
	Polymer	Epoxy resin system		8.537	15.0	19.7145
	Filler	Silicon Dioxide (SiO2)	14808-60-7	21.05794	37.0	48.6291
	Flame retardant	Antimony Trioxide (Sb2O3) - cas no. 1309-64-4	1309-64-4	0.28457	0.5	0.65715
Subtotal				56.91335	100	131.43
Wire	Pure metal	Copper (Cu)	7440-50-8	0.00866	100.0	0.02
	Subtotal			0.00866	100	0.02
Total				100.00001	100	230.93

Disclaimer

All information in this document is furnished for exploratory or indicative purposes only. All information in this document is believed to be accurate and reliable. However, WeEn Semiconductors does not give any representations or warranties as to the accuracy or completeness of such information and shall have no liability for the consequences of use of such information. WeEn Semiconductors may make changes to information published in this document at any time and without notice. Minor deviations may occur in the products from different manufacturing location. This document supersedes and replaces all information supplied prior to the publication hereof. Nothing in this document may be interpreted or construed as an offer to sell products that is open for acceptance or the grant, conveyance or implication of any license under any copyrights, patents or other industrial or intellectual property rights.